



5900 Success Drive, Rome, New York, 13440
Phone: 888-NORTEK7 (667-8357), Fax: 315-337-4587

Technical Data Sheet

General Description

PRODUCT CODE:	Q6SK252
PRODUCT NAME:	ANSI 70 GRAY SDC
CHEMISTRY:	SUPER- DURABLE POLYESTER
SURFACE FINISH:	SMOOTH

Application Recommendation

Surface preparation: All oil and grease, scale and rust, must be removed.
 Pretreatment Requirements: A five stage pretreatment according to ASTM B449 is highly recommended, Chrome-free pretreatment according to AAMA 2604-05 are acceptable methods of optimum adhesion performance and excellent corrosion protection.
 Cure Schedule 10 min. at 400 Deg. F or 15 min. at 375 Deg. F, metal temperature.
 Film thickness: 4-5 mils.
 Features: **Q-Series** is Nortek's line of one coat application Super Durables powder coating with superior corrosion resistance, formulated to exceed the stringent requirements of AAMA 2604-02 specification (American Architectural Manufacturers Association). Superior gloss and color retention, excellent weather resistance, Excellent mechanicals properties, Excellent edge coverage, good storage stability.
 Typical Applications: All Architectural and construction application including Playground equipment, Agricultural equipment and Marine application.
 Shelf life is expected to be at least one year from date of shipment when stored in dry conditions at less than 80 Deg. F.(27 Deg. C.)

Typical Performance Characteristics

Specific Gravity	Calculated	1.55
Coverage	Calculated	124 squares foot/lb./mil
Particle Size	ASTM D3451	0-10% over 200 Mesh
	Alpine Jet Sieve	40-45% over 400 Mesh
Gloss 60 Degree	ASTM D 523	90+/-5 units
Impact Resistance	ASTM D 2794	160 in. lbs. Direct/160 in.lbs. Reverse
Flexibility	ASTM D 522	Pass 1/8" Mandrel
Pencil Hardness	ASTM D 3363	>2H
Adhesion	ASTM D 3359	5B- Method B
Dielectric Resistance	ASTM D 149	1000 volts per mil
Salt Spray Resistance	ASTM B 117	3000 hr. (ASTM D165 Creepage Min.7)
		(ASTM D714 Blister Min. 8)
Humidity Resistance	ASTM D 2247	3000 hr.(ASTM D714 Blister Min. 8)

Weathering: South Florida Exposure 45 degree angle facing South

Color Retention 5 years (ASTM D2244)	< 5 DE "CIELAB"(ASTM2244)
Chalk Retention 5 years (ASTM D659)	Minimum 8 rating(ASTM D659)
Gloss Retention 5 years (AAMA 2604)	> 30% retention(ASTM D523)
Erosion retention 5 years (ASTM D662)	<10% Loss

Important Warranty and Disclaimer: The information contained herein is to the best of our knowledge, true and accurate. All recommendations or suggestions for use are made without guarantee, since the conditions of use are beyond our control. The performance characteristics of these products vary according to product application, operating conditions, and materials applied to. Since these factors can affect results, we recommended that you perform your own test to determine to your satisfaction whether the product is acceptable and is suitable for your particular purpose under your own operating conditions prior to using any product in full scale production. Seller warrants the product to be free from defects in materials and workmanship. Such warranty is exclusive and is in lieu of any other warranty. Nortek Corporation disclaims any liability incurred in connection with the use of our products and information contained herein. No representative of ours has authority to waive or change these provisions, which applies to all product sales.
