



5900 Success Drive, Rome, New York, 13440  
Phone: 888-NORTEK7 (667-8357), Fax: 315-337-4587

## Technical Data Sheet

### General Description

PRODUCT CODE: S8SK166  
PRODUCT NAME: RAL 7044 SILK GRAY  
CHEMISTRY: POLYESTER SUPER- DURABLE  
SURFACE FINISH: SMOOTH

### Application Recommendation

Surface preparation: All oil and grease, scale and rust, must be removed.  
Pretreatment Requirements: A five stage pretreatment according to ASTM B449 is highly recommended, Anodizing according to AAMA 2603-02 and Chrome-free pretreatment according to AAMA 2604-05 are acceptable methods of optimum adhesion performance and excellent corrosion protection.  
Cure Schedule 10 min. at 400 Deg. F, or 15 min. at 375F metal temperature.  
Film thickness: 3-5 mils.  
Features: Superior gloss and color retention, excellent weather resistance, excellent mechanicals properties, excellent edge coverage, good storage stability.  
Typical Applications: All Architectural and construction application including Playground equipment, Agricultural equipment and Marine application.  
This powder coating do not contain the 10 restricted substances, as defined in the European directive 2015/863/EU (RoHS 3 restriction of Hazardous Substances) 2), Article (4)2, Annex II, to this product, and have determined that any impurities disclosed to us by our suppliers are in amounts less than the maximum concentration values tolerated by weight in homogeneous materials for the restricted hazardous substances under the RoHS 3 CE- marking directive and REAC Restricted Chemical list , Cadmium, Chromium VI, Lead, Mercury, Cadmium, Polybromobiphenyls, Polybrominatedbiphenyls(PBB) under the RoHS 3 compliance effect July, 2019 Do not contain Chemicals listed in California January 03, Proposition 65 list  
Shelf life is expected to be at least one year from date of shipment when stored in dry conditions at less than 80 Deg. F.(27 Deg. C.)

### Typical Performance Characteristics

Specific Gravity	Calculated	1.60
Coverage	Calculated	120 squares foot/lb./mil
Particle Size	ASTM D3451	0-10% over 200 Mesh
	Alpine Jet Sieve	40-45% over 400 Mesh
Gloss 60 Degree	ASTM D 523	85+/-5 units
Impact Resistance	ASTM D 2794	160 in. lbs. Direct/160 in.lbs. Reverse
Flexibility	ASTM D 522	Pass 1/8" Mandrel
Pencil Hardness	ASTM D 3363	>2H
Adhesion	ASTM D 3359	5B- Method B
Salt Spray Resistance	ASTM B 117	3000 hr. (ASTM D165 Creepage Min.7)
		(ASTM D714 Blister Min. 8)
Humidity Resistance	ASTM D 2247	3000 hr. (ASTM D714 Blister Min.8)

### Weathering: South Florida Exposure 45 degree angle facing South

Color Retention	5 years (ASTM D2244)	< 5 DE "CIELAB" (ASTM D2244)
Chalk Retention	5 years (ASTM D4214)	Minimum 8 rating (ASTM D659)
Gloss Retention	5 years (AAMA 2604)	> 30% retention (ASTM D523)
Erosion retention	5 years (ASTM D662)	<10% Loss

**Important Warranty and Disclaimer:** The information contained herein is to the best of our knowledge, true and accurate. All recommendations or suggestions for use are made without guarantee, since the conditions of use are beyond our control. The performance characteristics of these products vary according to product application, operating conditions, and materials applied to. Since these factors can affect results, we recommended that you perform your own test to determine to your satisfaction whether the product is acceptable and is suitable for your particular purpose under your own operating conditions prior to using any product in full scale production. Seller warrants the product to be free from defects in materials and workmanship. Such warranty is exclusive and is in lieu of any other warranty. Nortek Corporation disclaims any liability incurred in connection with the use of our products and information contained herein. No representative of ours has authority to waive or change these provisions, which applies to all product sales.